

Experimental Analysis & Designing of Fabrication Method of Shear Fatigue Strength of Glass Fiber Epoxy and Chapstan E-Glass Epoxy Laminates

Pns Srinivas¹, Movva Mounika², M.Rajya Lakshmi³.

¹. M.Tech pvp Siddhartha institute of engineering & technology,kanuru,vijayawada.

². Asst Professor Of Mechanical Department In pap Siddhartha institute of engineering & technology,kanuru,vijayawada

³. Asst Professor Of Mechanical Department In pvp Siddhartha institute of engineering & technology,kanuru,vijayawada

ABSTRACT

The present project work mainly is focusing on development of manufacturing process and establishing critical test procedures for the polymer reinforced composite materials to be used in automobile & power plant equipments. This experiment played an important role in estimation of stiffness of the laminate which in turn helps for the testing to evaluate the stiffness of the laminate for further mathematical analysis. The evaluating elastic properties and the flexural stiffness of the composite beam by theoretical calculation is compared with experimental value analysis and from which the relations of mechanical properties are derived. This reduction in stiffness can further be improved by advanced manufacturing process such as compressor moulding, macro sphere moulding & auto clave moulding and the results obtained from the analytical testing are used to calibrate the load transducers. The load transducer shows a linear response to the load from this is clearly evident that the testing could be able to generate the useful data for evaluating the fatigue failure behavior of the composites. The data acquisition system from standard manufacturer of model TSI-608 which exactly meets requirements. A continuous plot of time verses load could be obtained We can say that the required data can be generated as per expectations, which could be utilized to establish the fatigue failure behavior any kind of composite laminate.

KEYWORDS: glass epoxy composites, fatigue test rig, transducer, pressure plate, CATIA

I. INTRODUCTION

The laminated composite materials usage is increasing in all sorts of engineering applications due to high specific strength and stiffness. Fiber reinforced composite materials are selected for weight critical applications and these materials have good rating as per the fatigue failure is concerned. Present work is aimed to analyze the behavior of each laminate under the flexural fatigue test rig. Therefore here different types of composite materials are selected for test specimens. For this load transducer, the accuracy level required in transducer body is an important task. As selection of a transducer and work for its consistency is important consideration. Therefore a sensitive, consistently strong transducer to meet the axial tension-compression fatigue loading is required. (2)To provide dynamic sensibility to the transducer, foil type resistance strain gauges are used. The geometric shape of the load transducer is an important factor to be considered, to impart sufficient strain to the strain gauge, which in turn generates a noticeable signal with noticeable amplitude in the form of a voltage signal. The dynamic nature of loading could be read in the form of a signal is possible only with the iso-elastic type of strain gauges. In order to get the information after which it fails software is created which produces the waves depicting the response of the transducer to the loads applied on it. The present project work mainly is focusing on development of manufacturing process and establishing critical test procedures for the polymer reinforced composite materials to be used in certain engineering applications.

II. FATIGUE

The flexural fatigue failure in laminated composite materials is a very common failure mode in most of the FRP components. As reinforced polymers used in weight critical applications, often over designed to compensate fatigue failure lead to the increase in weight which in turn hampers the objective of designer. In this

connection the investigation on flexural fatigue failure behavior of laminate to be used in the component is very important. As standard equipment and test procedures are not available.

2.1 Fatigue

When a material is subjected to repeated stresses or loads, it fails below the yield stress. Such type of failure of a material is known as fatigue.

2.1.1 Characteristics of Fatigue

- In metals and alloys, the process starts with dislocation movement, eventually forming persistent slip bands that nucleate short cracks.
- Fatigue is a stochastic process, often showing considerable scatter even in controlled environments.
- The greater the applied stress range, the shorter the life.
- Fatigue life scatter tends to increase for longer fatigue lives.
- Damage is cumulative. Materials do not recover when rested.
- Fatigue life is influenced by a variety of factors, such as temperature, surface finish microstructure, presence of oxidizing or inert chemicals, residual stresses, contact, etc.

2.2 Flexural Fatigue

When a material is subjected to variable bending stresses or loads, it fails below the yield stress.

2.3 Fatigue Test Applications

Fatigue testing helps determine how a material or product design will perform under anticipated service conditions. Many fatigue tests repeat the application of loads by controlling stress that is repeated for millions of cycles. In many engineering applications, products or materials experience vibration or oscillatory forces so it's important to predict and prove fatigue life, or cycles to failure under loading conditions. There are as many specialized fatigue testing protocols or test methods as there are products designed for fatigue applications. A few are supported as industry standard test methods but most designs are unique so machines are configured to match their needs. Metals and metal substitutes such as advanced composites are commonly used for fatigue resistant designs, so standards are more available. Low Cycle Fatigue (LCF) or strain controlled tests, High Cycle Fatigue (HCF) or load controlled tests, and even Random Spectrum tests are now common. Medical implants for orthopedic and intravascular use are also widely tested to FDA requirements.(4)

2.4 Mechanism of Fatigue Failure in Laminated Composites

“Composites are a combination of a reinforcement fiber in a polymer resin matrix, where the reinforcement has an aspect ratio that enables the transfer of load between fiber, and the fibers are chemically bonded to the resin matrix. This precise definition accounts for the attributes of composites as an engineering material and differentiates them from a lot of combined materials having a lesser degree of synergy between the individual components. Cyclic deformation process in fiber-reinforced materials differs widely from those in homogenous isotropic materials. For example, crack nucleation plays a significant role in the latter; in the former, cracks and failure zones are often formed in the very first few cycles. In fact, there are often voids and defects in the material even before cycling begins. Secondly, fiber reinforced materials are characterized by a high degree of anisotropy; the ratio of longitudinal to transverse moduli varies from about 5 for glass fiber-polymers to about 25 for graphite or boron fiber-polymers. The stress field around a flaw in such a highly anisotropic medium is significantly different from one in isotropic material consequently, while homogeneous isotropic materials usually fail in fatigue by the nucleation of a crack which propagates in single mode, composite materials generally exhibit a variety of failure modes including matrix crazing or micro cracking, individual fiber failures resulting from statistically distributed flaw strengths, debonding, delamination, void growth etc. In addition, several of these failure modes are generally present at any given time prior to failure.

Further, failure mechanisms in the fiber are different from those in the matrix. It is well established, for example, the glass by itself does not exhibit dynamic fatigue failure but fails in „static „ fatigue as a result of thermally activated stress corrosion reactions of water vapor at surface flaws. When glass fiber are enclosed in a polymer matrix, and subjected to cyclic loading, it is not clear whether there would be reactions at the entire glass polymer interface due to moisture absorption through the polymer layer, or whether matrix micro cracks, alone (resulting from cyclic failure), would provide a conduit for preferential attack by water vapor over a localized area on the fibers at the crack front leading to further crack growth and eventual fatigue failure of the composite.(5) From this description it is clearly evident that the fatigue life of composite laminate is influenced

by many factors. The degree of significance of the above mentioned factors cannot be established with confidence. This present work is aimed at establishing a suitable test procedure for the fatigue life characteristics with a low cost test rig to meet the real time design requirements. The features of the test rig are explained in following script. As the test proceeds for so many number of load cycles (is of order 10^6 cycles) the generated from dynamic transducer cannot record manually. Then the signal conditioning system coupled with analog to digital conversion electronic circuit and the data logging software incorporated in the test rig. This logged data can be analyzed to establish the failure behavior and fatigue life characteristics of the composite laminates. This method of testing can be utilized for fatigue applications.



Fig 1. Positioning of composite material in vertical direction in Pictorial view of Fatigue Test Rig



Fig 2. Positioning of composite material in horizontal direction in Pictorial view of Fatigue Test Rig

The Bending fatigue test rig is capable of simulating bending fatigue load of 0 to 1000N on the test coupon at a frequency of 94 cycles per minute. The king pin is assembled to the dovetail mechanism which could be fixed at desired eccentricity. That provides desired bending force on the specimen.

2.5.1 Important Components of Test Rig

- [1] Load cell
- [2] Specimen holding beam
- [3] Dovetail assembly
- [4] Induction motor
- [5] Adjustable columns(Sliding)
- [6] Electronic circuit(Signal Conditioning System)
- [7] Data acquisition software
- [8] Connector from the electronic circuit to the computer. Printer(7)

2.5.2 Working Principle of Test Rig

The schematic diagram of test rig as shown in Fig. 3.2. is self explanatory. The hinge eccentricity from the center of the crank is directly proportional to the deflection of the composite specimen. And this deflection resisting force is experienced by the linkage which is equipped with strain measurement. The strain gauge bonded to the linkage (load cell) elongates and contracts along with the load cell which in turn imbalances the balanced bridge circuit connected to the strain gauge. The output voltage of the bridge circuit is directly proportional to the deflection load of the composite specimen. As crank rotates with the constant rpm of 94 the strain measuring system develops voltage proportional to the degree of deflection. The voltage waveform is a pure sine wave. The cyclic load applied to the composite specimen generates a fatigue crack at the fixed end A from the Fig. 2.2.




Fig.3. Schematic line diagram of Hinge Eccentricity, Load Cell and Specimen Holding Arrangement

Which in turn reduces the stiffness of the composite specimen and that is been clearly reflected on the voltage output from the strain measuring bridge circuit. The amplitude of wave form decreases as the damage progresses in the due course as the cyclic loading proceeds from 0 cycles to n number of cycles. This diminishing wave form reveals the health of the laminate as the time progresses. The recording of data in digital form could lead to analyze the fatigue damage pattern accurately. (9)

3.5.3 Specifications of the Test Rig

| | | |
|-------------------------|-------|----------------|
| Bending load capacity | ----- | 0 to 1200N |
| Frequency | ----- | 1.57 to 10 RPS |
| Specimen specifications | ----- | 200x40x6 mm |
| Eccentricity | ----- | 0 to 250 mm |

III. LOAD CELL

Introduction: Load cell is a very important component which senses load and delivers a voltage analog signal, which is proportional to the intensity of load. This consists of a metallic body designed to meet the requirements of the working load range, generally it is made of aluminum alloy. The foil type strain gages are fixed to the body of the load cell. When the body of the load cell is subjected to load, the strain induced is transmitted to the strain gage. Dynamic load sensor (LOAD CELL) is important component of the test rig.(10)

Selection of a Transducer:

The selection of the correct load transducer is followed by the following steps:

1. Material selection.
2. Proposing geometric models.
 - ❖ High sensitive type
 - ❖ Medium sensitive type

The material selection is based on the elastic property that is young's modulus. This should be capable of providing sufficient elastic strain for a given load application range. As per the present load application range of 0 -1000 N the material selected for this application is an aluminum alloy of Young's modulus 70 GPA.

a. High Sensitive Type Load Cells

Ring type load cell: The ring type load cell body is made of Aluminum. This is proposed in view of simulating more strain in the segments of hollow cylindrical segments, when the body is subjected to tensile and compressive stress. The ring type load cell is furnished in Fig. 4.1. The ring portion of the load cell body is first part of the body to undergo strain by virtue of changing its shape, which is a perfect circular to oval shape. When the load cell is subjected to tensile load, the inner portion of the body is subjected to tensile strain and the outer portion is subjected to compressive strain. This is proposed in the view of gaining strong signal from the bridge circuit.





Fig. 4. Ring Type Load Cell

Fig. 5. C-Type Load Cell

“C” type load cell: The C type load cell is supposed to be strained in the thinner portion of the body. **b. Medium Sensitive Type Load Cells**

H-Type Load Cell: “H” type of load cell body is proposed to meet the dynamic loading situation of the flexural fatigue test rig.





Fig. 6. H-Type Load Cell

Fig.7.-Type Load Cell

“I” Type Load Cell: “I” type load cell having the thinnest gauge portion among the proposed load cell body models.

Pillar Type Load Cell: Among the load cell bodies proposed are observed carefully, and then the cylindrical gauge portion is proposed in view of achieving same strain on the gauge bonding area of the load cell body.




Fig.8. Pillar Type Load Cell

IV. ELECTRONIC CIRCUIT

Introduction: The electronic circuits are also very important a component of system and this are capable of amplifying the analog signal coming from the load cell and digitizes it to have provision of storing the data accurately to analyzing the data regarding stiffness degradation behavior of the specimen.

4.1 Electronic Circuit for Signal Conditioning and Data Logging Systems

Dynamic load sensing is a mechanism, which senses the fluctuating loads with respect to time. A load cell (strain gage type) is a transducer, which senses the varying loads and changes its dimensions proportional to stress. The strain gage is incorporated in the bridge circuit and change in its resistance due to strain will unbalance the bridge. This unbalance voltage is amplified by the instrumentation amplifier. (12)A real time application of dynamic load sensing which convert the analog voltage from instrumentation amplifier to digital voltage by an ADC. This digital voltage is fed to computer via USB port. The sensing element which is an electrical type load cell senses the strain. The strain gage is glued to the load cell. The resistance of the load cell is 350 ohms resistors. This bridge is excited by the 10volts DC supply. Under no load condition i.e., when strain gage is not strained the bridge is under balanced condition. When load is applied on the load cell, the dimensions of strain gage gets changed thereby its resistance is varied. The amount of strain applied on the load cell proportionally changes the resistance of the strain gage. This change in resistance causes the bridge to unbalance. (13)This unbalanced voltage is proportional to the load applied on the specimen. In the first stage of amplification the gain has been limited to only 100 even though the capability of AD620AN is having a gain of 1000. This decision has been taken by carefully observing characteristics of the instrumentation amplifier to avoid unnecessary interference. The typical circuit to the signal conditioning system is shown in following Fig. 5.1.




Fig 9.Signal conditioning circuit layout

V. EXPERIMENTATION

Introduction to Flexural Fatigue Experimentation

The present experimentation is aimed to understand the flexural fatigue behavior under high cycle fatigue conditions of Glass Fiber Epoxy, Chapsten E-Glass Epoxy and Glass Fiber Polyester Epoxy laminates. Before getting into the experimentation work, the evaluation of mechanical properties of glass fiber epoxy laminates is very important. A laminates of 200mm length, 40mm width and 6mm thickness were prepared. And from this laminates tensile tests were conducted for calculating the starting load on specimens for conducting fatigue test.

5.1 Loading Criteria for Flexural Fatigue Analysis of Glass Fiber Epoxy Laminates

For simulating high cycle flexural fatigue on test coupons, the calculations were made to estimate the bending loads considered to simulate stresses of the order of 50% of maximum tensile strength. To estimate the bending load, tensile tests were carried out on laminates. The tensile test results of specimens of Glass fiber epoxy, Chapsten E-glass epoxy and Glass fiber polyester epoxy are furnished in table No. 6.1.

And the corresponding bending loads to be applied are calculated with reference to the beam bending equation. $M/I = F/Y$

The specimen is fixed to fatigue testing rig in cantilever mode, then the Maximum bending moment $M = WL$ where W is the bending load applied on the specimen. The distance from the neutral axis to the surface of specimen is Y , which is equal to half the thickness of the specimen.

$$Y = t/2$$

Moment of Inertia of the specimen $I = bh^3/12$ and Bending stresses induced in the specimen

$F = 1/2(\text{Ultimate Tensile strength of the specimen})$ From the above theory, bending load for each specimen is obtained.

a) Metallic Mould

The mould is made of MS material. To prevent the leakage of resin, four dams were fixed through nuts and bolts on a 10 mm thick MS plate which is machined by facing operation on lathe machine. The mould cavity area is 300X300 mm²

The mould with above specifications as shown in the figure 6.1. The required pressure is applied through pressure plate by tightening the nuts and bolts, the arrangement of which is shown in figure 6.2.



Fig. 10. Representation of Mould



Fig. 11. Representation of Pressure Plate

b) Pressure Plate

20 mm thick MS pressure plate with flat turned surface finish ensuring perfect flatness is used in order to prevent crippling and flexing due to compressive forces produced due to the top cover plate.

With the above mentioned precautions a laminate, of good quality can be made as shown in figure 6.3. From this laminate the test coupons are cut with required specifications which have already been discussed.




Fig 12. Laminate Moulded from the Metallic Mould by Compression Moulding Technique

5.2 Tensile Tests

Tensile tests are performed on the specimens and the tabulated values are furnished in table 6.1. The specifications of the test specimen are 200mm length, 6mm thickness and 40mm width. Following figures related to tensile tests conducted on various specimens. The figure represents the tensile test in progress. The figures to furnish below are specimens subjected to tensile test.

| Specimens | Max strength(MPa) | Tensile |
|-----------------------------|-------------------|---------|
| Glass fiber epoxy | 358 | |
| Chapsten E-glass epoxy | 207 | |
| Glass fiber polyester Epoxy | 74.5 | |




Table 1. Tensile Test Results

Fig. 13. Tensile Test in Process



Fig. 13.1 Tensile Test Specimens of Glass Fiber Epoxy, Chapsten E-Glass Epoxy and Glass Fiber Polyester Epoxy




Fig. 13.2 Glass Fiber Epoxy Specimen after Tensile Test



Fig 13.3 Chapsten E-Glass Epoxy Specimen after Tensile Test



Fig. 13.4 Glass Fiber Polyester Epoxy Specimen after Tensile Test

VI. RESULTS AND DISCUSSIONS

Introduction

The present project work is aimed at establishing certain mechanical properties while designing fiber reinforced components for engineering applications. This experiment played an important role in estimation of stiffness of the laminate which in turn helps the user of the testing to evaluate the stiffness of the laminate for further mathematical purposes. The evaluating elastic properties and estimating the flexural stiffness of the composite beam and from the analytical evaluation of flexural stiffness has been matched with the theoretical calculations. This loss in stiffness of composite laminate is due to inherent defects generally occurs during welding and curing of the reinforced component. This reduction in stiffness can further be improved by advanced manufacturing process such as compressor moulding and auto clave moulding and the results obtained from the analytical testing are used to calibrate the load transducers. The load transducer shows a linear response to the load from this is clearly evident that the testing could be able to generate the useful data for evaluating the fatigue failure behavior of the composites. This data acquisition load generates the digital of time verses voltage by converting this data into time verses voltage with suitable multiplying factors. The data acquisition system from standard manufacturer of model pci-207 which exactly meets requirements. A continuous plot of time verses load could be obtained. We can say that the required data can be generated as per expectations, which could be utilized to establish the fatigue failure behavior any kind of composite laminate.

6.1 Flexural Fatigue Failure Behaviour of Glass Fiber Epoxy Laminate

Flexural fatigue failure behavior of laminates exhibits stiffness decay with respect to number cycles of load application. In this work ORIGIN LAB curve fitting tool is used to plot the data, number of cycles verses instantaneous maximum bending load within the cycle. The total scheme of experimentation is conducted at constant amplitude of bending. This phenomenon of bending load for yielding constant deflection is also known as stiffness. The test specimen used is shown in Fig. 7.1.



Fig. 14. Glass Fiber Epoxy Test Specimen

From the data logging system, the converted data is load applied on the specimen and number of cycles is given in the table 7.1. This data is used in plotting stiffness degradation curves.

Table 2. Stiffness Degradation Data of Glass Fiber Epoxy laminate

| Number of Cycles | LOAD in NEWTONS | | | | |
|------------------|-----------------|----------|---------|----------|---------|
| 0 | 320.006 | 5096.22 | 168.473 | 14894.6 | 116.910 |
| 100.48 | 311.663 | 5532.68 | 168.306 | 15305.93 | 114.223 |
| 219.8 | 291.354 | 4981.61 | 164.48 | 15769.08 | 113.781 |
| 345.4 | 281.055 | 6055.49 | 163.633 | 16552.51 | 113.09 |
| 405.06 | 278.333 | 6305.12 | 163.08 | 17397.17 | 113.046 |
| 538.51 | 278.356 | 6355.36 | 162.17 | 18012.61 | 111.728 |
| 591.89 | 270.37 | 6466.83 | 160.97 | 18552.7 | 108.632 |
| 676.67 | 267.555 | 6531.2 | 160.5 | 19196.4 | 104.075 |
| 797.56 | 267.553 | 6590.86 | 157.48 | 19915.45 | 100.07 |
| 904.32 | 264.895 | 6626.97 | 157.167 | 21078.82 | 95.11 |
| 943.57 | 262.481 | 6653.66 | 154.957 | 22000.41 | 88.041 |
| 1029.92 | 242.97 | 6686.63 | 152.7 | 22564.04 | 87.966 |
| 1146.1 | 234.243 | 6714.89 | 152.586 | 23242.28 | 84.687 |
| 1890.28 | 226.802 | 6749.43 | 152.16 | 23831.03 | 83.902 |
| 2138.34 | 225.75 | 6772.98 | 150.94 | 24287.9 | 77.38 |
| 2474.32 | 223.974 | 6821.65 | 150.982 | 24689.82 | 73.771 |
| 2701.97 | 221.938 | 7380.57 | 149.333 | 25170.24 | 70.9 |
| 2739.65 | 219.28 | 7567.4 | 148.687 | 25481.1 | 68.147 |
| 2797.74 | 206.40 | 7892.4 | 145.935 | 25865.75 | 67.971 |
| 2824.43 | 202.321 | 8262.91 | 145.701 | 25906.57 | 65.935 |
| 2964.16 | 198.327 | 8700.94 | 142.19 | 26602.08 | 65.77 |
| 3058.36 | 195.506 | 9132.7 | 140.777 | 27245.78 | 65.16 |
| 3110.17 | 193.661 | 9679.05 | 137.973 | 28164.23 | 63.473 |
| 3303.28 | 185.08 | 9964.8 | 137.25 | 29088.96 | 62.413 |
| 3496.39 | 182.853 | 10489.17 | 133.216 | 29665.15 | 62.03 |
| 4114.97 | 179.851 | 11366.8 | 132.632 | 30506.67 | 60.127 |
| 4491.77 | 177.786 | 11999.51 | 130.713 | | |
| | | 12767.24 | 126.624 | | |
| | | 13547.53 | 125.163 | | |

The data obtained from the experiments is plotted in Fig. 7.2. Results obtained reveal that the nature of behavior of the material is revealing exponential decay in its mechanical properties due to fatigue. This type of plotting is normally known as “Stiffness Degradation Curve plotting”. From the figure it is clear that the bending load is dropped from

320N to 60.127N and attained pivoting state where further reduction in stiffness is not noticed. Pivoting state is noticed at 25,000cycles.





Fig. 14.1 Stiffness Degradation behaviour of Glass Fiber Epoxy laminate Number of Fatigue Cycles at 1.57 RPS for Glass Fiber Epoxy Laminate

Fig. 14.2 Second order differential curve of Glass Fiber Epoxy laminate derived from Fig.

7.2 Flexural Fatigue Failure Behaviour of Chapsten E-Glass Epoxy Laminate




Table 3. Stiffness Degradation Data of Chapsten E-Glass Epoxy laminate

| Number of Cycles | LOAD in NEWTONS | 7353.88 | 79.787 | 18454.02 | 34.801 |
|------------------|-----------------|----------|--------|----------|--------|
| 0 | 318.764 | 7523.44 | 74.421 | 18977.65 | 34.46 |
| 65.94 | 203.285 | 7656.89 | 71.113 | 19501.28 | 34.12 |
| 202.53 | 122.103 | 8247.21 | 68.1 | 20024.91 | 33.775 |
| 244.92 | 120.388 | 8597.32 | 65.6 | 20548.54 | 33.433 |
| 281.03 | 119.051 | 8685.24 | 54.7 | 21072.17 | 33.091 |
| 310.86 | 115.772 | 8859.51 | 47.73 | 21595.8 | 32.75 |
| 438.03 | 110.53 | 8913.43 | 46.77 | 22119.43 | 32.406 |
| 477.28 | 108.383 | 8962.47 | 45.356 | 22643.06 | 32.064 |
| 507.11 | 107.142 | 9014.62 | 44.756 | 23166.69 | 31.722 |
| 582.47 | 105.698 | 9452.74 | 43.9 | 23690.32 | 31.38 |
| 610.73 | 104.392 | 9924.73 | 42.235 | 24213.95 | 31.04 |
| 723.77 | 102.612 | 10732.22 | 41.766 | 24755.32 | 30.7 |
| 761.45 | 101.331 | 11219.35 | 40.565 | 25296.69 | 30.354 |
| 1339.21 | 98.353 | 11763.48 | 39.96 | 25838.06 | 30.112 |
| 1734.85 | 97.95 | 12132.83 | 38.91 | 26379.43 | 29.67 |
| 2391.11 | 97.62 | 12764.03 | 38.565 | 26290.8 | 29.33 |
| 2634.46 | 97.21 | 13217.72 | 38.223 | 27462.17 | 28.985 |
| 3367.65 | 96.73 | 13741.35 | 37.881 | 28003.54 | 28.643 |
| 4461.94 | 94.842 | 14264.98 | 37.54 | 28544.91 | 28.3 |
| | | 14788.61 | 37.2 | 29086.28 | 27.96 |

Fig. 15. Chapsten E-Glass Epoxy Test Specimen

The Flexural fatigue analysis data obtained from the experiment for Chapsten E-glass epoxy laminate is given in table 7.2. And the stiffness degradation is plotted in Fig.7.5. From this figure it is observed that the bending load dropped from 318.764N to 27.416N. Compared to Glass fiber epoxy specimen stiffness degradation curve, it is observed that there is smooth reduction in stiffness. The stiffness at the pivoting state is 27.416N as per the experiment. The stiffness of the specimen at the pivoting state is 8.6% of the virgin specimen.





Fig. 16.1. Stiffness Degradation behaviour of Chapsten E-Glass Epoxy laminate Number of Fatigue Cycles at 1.57 RPS for Chapsten E-Glass Epoxy Laminate.

Fig. 16.2. Second order differential curve of Chapsten E-Glass Epoxy laminate derived from Fig. 6.5.

The experiments carried out in the laminates of Glass Fiber Epoxy, Chapsten E-Glass Epoxy and Glass Fiber Polyester Epoxy clearly exhibited a variation in the residual load bearing capacity after pivoting state. The graphical representation in Fig. 16.1. The stiffness degradation process of each specimen under goes basically in three stages, in the first stage the stiffness reduction rate is very fast this is due to the top and bottom layers of the laminates are subjected to maximum strain which leads to the failure being the glass reinforcement is pure elastic in nature. In the second stage as the stress levels on the subsequent layers reduces as the distance from the neutral layer is continuously decreasing. In the third stage of the failure already broken fibers provides a cushioning effect and resist the free bending of the specimen hence the stiffness degradation tends to towards zero. The results clearly establishes that the Glass Fiber Polyester Epoxy, exhibited very slow stiffness reduction rate when compared to the other specimens and the residual bending load bearing (residual stiffness) is also maximum i.e. 58.617N and the Stiffness retention after pivoting state is 73.26%. Hence it can be recommends that the Glass Fiber Polyester Epoxy material is best for fatigue critical applications.




Fig. 16.3. Consolidated Flexural Fatigue Test Results of Glass Fiber Epoxy, Chapsten E-Glass Epoxy and Glass Fiber Polyester Epoxy laminates.

VII. CONCLUSION

From the experimental investigation:

1. Flexural fatigue failure behavior of Glass Fiber Polyester Epoxy laminate composite exhibited better results.
2. The results clearly establish that the Glass Fiber Polyester Epoxy laminate exhibited very slow stiffness reduction rate when compared to the other specimens.
3. The residual bending load (residual stiffness) is also maximum i.e. 58N and the Stiffness retention after pivoting state is 72.5% of the virgin specimen.
4. Hence it can be recommended that the Glass Fiber Polyester Epoxy laminate is good for flexural fatigue critical applications such as wind turbine blades, Air craft wing and auto motive leaf spring constructions.

REFERENCES

- [1] Saud Aldajah Ammar Al-omari and Ashraf Biddah Accelerated weathering effects on the mechanical and surface properties of CFRP composites Vernon T. Bechel, John D. Camping, Ran Y. Kim
- [2] 2. Cryogenic/elevated temperature cycling induced leakage paths in PMCs Composites Part B: Engineering, Volume 36, Issue 2, March 2005
- [3] Sandhya Rao, RMVGK Rao Cure studies on bifunctional epoxy matrices using a domestic microwave oven Polymer Testing, Volume 27, Issue 5, August 2008
- [4] S. Birger, A. Moshonov, S. Kenig The effects of thermal and hygrothermal ageing on the failure mechanisms of graphite-fabric epoxy composites subjected to flexural loading Composites, Volume 20, Issue 4, July 1989
- [5] [5]Mechanical Properties Of Composite Material Using Natural Rubber With Epoxy Resin Dr. Hani Aziz Ameen 9/3/2008
- [6] Fatigue Strength Assessment Of A Short Fibre-Reinforced Plastic Based On The Energy Dissipation G. Meneghetti*, M. Quaresimin**, M. De Monte**
- [7] Experimentally Investigation Effect Of Geometrical Cross- Section On Fatigue Strength Of Aluminum Alloy (6063) Ghazi S. Al-Marahleh and Khaleel Abushgair Received: July 19, 2010
- [8] Fatigue and Ultrasonic Testing of Epoxy-Glass Composites M. Rojek, J. Stabik*, S. Sokól
- [9] Mechanical Measurements by Thomas G.Beckwith, Roy D. Marangoni, John H. Lienhard Fifth edition an imprint of Addison Wesley Longman, Inc First ISE reprint 1999
- [10] The Pressure and Strain Handbook, Vol.29, Omega Engineering.