

# Effect of Chopped Glass Fibers On The Strength Of Concrete Tiles

Honey Mishra<sup>1</sup>, Nilima Baisakhi<sup>2</sup>

<sup>1</sup>Assistant Professor, Department of Civil Engineering, Gandhi Institute For Technology (GIFT), Bhubaneswar

<sup>2</sup>Assistant Professor, Department of Civil Engineering, Gandhi Engineering College, Bhubaneswar

## ABSTRACT

The effect of glass fibre on flexural strength, split-tensile strength and compressive strength was studied for different fibre content on M-20 grade concrete designed as per IS 10262. The maximum size of aggregates used was 20mm. To study the effect on compressive strength, flexural strength, split-tensile strength 6 cubes, 6 prisms and 6 cylinders were casted and tested. After that a practical application of GFRC in the form of cement concrete tiles was taken into consideration and no special technique was used to produce this tiles. The thickness of the tiles was 20mm and maximum size of aggregates used was 8mm. The water cement ratio was kept consistent and the admixture content was varied from 0.8 to 1.5 percent to maintain slump in between 50mm to 100mm. The mix proportion used was 1:1.78:2.66. The size of short fibres used were 30mm and the glass fibres were alkali resistant. The effect of this short fibres on wet transverse strength, compressive strength and water absorption was carried out. Six full sized tiles 400mm\*400mm\*20mm were tested and the results recorded. Pulse velocity tests was also conducted.

**KEYWORDS:** Pulse Velocity, GFRC, Flexural Strength, Compressive Strength

## I. INTRODUCTION

### 1.1 General:

One of the most important building material is concrete and its use has been ever increasing in the entire world. The reasons being that it is relatively cheap and its constituents are easily available, and has usability in wide range of civil infrastructure works. However concrete has certain disadvantages like brittleness and poor resistance to crack opening and spread. Concrete is brittle by nature and possess very low tensile strength and therefore fibres are used in one form or another to increase its tensile strength and decrease the brittle behaviour. With time a lot of experiments have been done to enhance the properties of concrete both in fresh state as well as hardened state. The basic materials remain the same but super plasticizers, admixtures, micro fillers are also being used to get the desired properties like workability, Increase or decrease in setting time and higher compressive strength.

Fibres which are applied for structural concretes are classified according to their material

As Steel fibres, Alkali resistant Glass fibres (AR), Synthetic fibres, Carbon, pitch and polyacrylonitrile (PAN) fibres.

### 1.2 Glass Fibre Reinforced Concrete:

Glass fibre reinforced concrete (GFRC) is a cementitious composite product reinforced with discrete glass fibres of varying length and size. The glass fibre used is alkaline resistant as glass fibre are susceptible to alkali which decreases the durability of GFRC. Glass strands are utilized for the most part for outside claddings, veneer plates and different components where their reinforcing impacts are required during construction. GFRC is stiff in fresh state has lower slump and hence less workable, therefore water reducing admixtures are used. Further the properties of GFRC depend on various parameters like method of producing the product. It can be done by various methods like spraying, casting, extrusion techniques etc. Cement type is also found to have considerable effect on the GFRC. The length of the fibre, sand/filler type, cement ratio methods and duration of curing also effect the properties of GFRC.

### 1.3 Applications:

The main area of FRC applications are as follows

- Runway, Aircraft Parking and Pavements
- Tunnel lining and slope stabilization

- Blast Resistant structures
- Thin Shell, Walls, Pipes, and Manholes
- Dams and Hydraulic Structure
- Different Applications include machine tool and instrument frames, lighting poles, water and oil tanks and concrete repairs.

#### **1.4 Advantages And Disadvantages of using Glass Fibers in Concrete:**

##### **1.4.1 Advantages:**

1. Lighter weight: With GFRC, concrete can be cast in thinner sections and is therefore as much as 75% lighter than similar pieces cast with traditional concrete. According to Jeff Girard's blog post titled, "The Benefits of Using a GFRC Mix for Countertops", a concrete countertop can be 1-inch thick with GFRC rather than 2 inches thick when using conventional steel reinforcement. A manufactured rock made with GFRC will measure a little portion of what a genuine rock of comparable extents would measure, taking into account lighter establishments and decreased delivering expense
2. High flexural strength, high strength to weight ratio.
3. Toughness: GFRC doesn't crack easily-it can be cut without chipping.

##### **1.4.2 Disadvantages:**

1. Durability: According to ACI 544.1R-96, *State of the Art Report on Fiber Reinforced Concrete*, "The strength of fully-aged GFRC composites will decrease to about 40percent of the initial strength prior to aging." Durability can be increased through the use of low alkaline cements and pozzolans.
2. GFRC as a material, however, is much more expensive than conventional concrete on a pound-for-pound basis.

#### **1.5 Present Investigation:**

The purpose of this research is to explore the compressive strength, split-tensile strength and flexural strength properties of concrete reinforced with short discrete fibers. The study was carried out on M-20 grade concrete the size of glass fibers used was 30mm and the fiber content was varied from 0% to 0.3% of the total weight of concrete. In studying the above three properties no admixture was used. Also the effect of glass fiber on cement and concrete tiles was studied whose fibre content was varied from 0% to 0.7% of the total weight of concrete. Cement and concrete are heavy duty tiles which are used at various places and are of practical use.

## **II. MATERIALS AND METHODS**

### **2.1 Materials:**

#### **2.1.1 Concrete:**

Concrete is the most widely used construction material. The basic materials of concrete are Portland cement, water, fine aggregates i.e. sand and coarse aggregates. The cement and water form a paste that hardens and bonds the aggregates together. Concrete in fresh state is plastic and can be easily moulded to any shape, as time passes it hardens and gains strength. The initial gain in strength is due to a chemical reaction between water and C<sub>2</sub>S and latter gain in strength is due to reaction between C<sub>3</sub>S and water. Concrete is produced by either following nominal mix proportions in which the mix proportions are fixed as per grade of concrete required or mix design proportions, latter produces more economical concrete.

In our work Portland slag cement (PSC) -43 grade Konark cement was used. Standard consistency, initial setting time, final setting time, 28-day compressive strength tests were carried out as per the Indian standard specifications. Clean river sand passing through 4.75 mm sieve was used as fine aggregates. The specific gravity of sand was 2.68 and grading zone of sand was zone 3 as per IS .Angular stones were used as coarse aggregates maximum size 20mm and specific gravity 2.72. Concrete was mixed and cured by ordinary water or tap water.

For casting cubes, cylinders and prisms maximum size of aggregate used was 20mm whereas in case of tiles the maximum size of aggregates used was 8mm. The water cement ratio used for concrete tiles was 0.45 and admixture was used to attain the desire workability.

#### **2.1.2 Cement :**

Cement is an extremely ground material having adhesive and cohesive properties which provide a binding medium for the discrete ingredients. The processes used for manufacture of cement can be classified as dry and wet.. The cement commonly used is Portland cement, it is also defined as hydraulic cement, i.e. a cement which hardens when it comes with water due to chemical reaction but there by forming a water resistant product. Portland cement is obtained when argillaceous and calcareous materials are grounded to fine powder

and mixed in definite proportion and fused at high temperature. When blast furnace slag is also used as one of the ingredients than the cement obtained is called Portland slag cement (PSC). Portland slag cement (PSC) – 43 grade (Konark Cement) was used for the experimental programme.

### **2.1.3 Fine Aggregates :**

Aggregates are generally obtained from natural deposits of sand and gravel, or from quarries by cutting rocks. The least expensive among them are the regular sand and rock which have been lessened to present size by characteristic specialists, for example, water, wind and snow and so on. The stream stores are the most well-known and are of good quality. The second most regularly used source of aggregates is the quarried rock which is reduced to size by crushing. The size of aggregates used in concrete range from few centimetres or more, down to a couple of microns. Fine aggregates is the aggregate most of which passes through a 4.75mm IS sieve and contains just that much coarser material as allowed by the IS details. The fine aggregate used for the experimental programme was obtained from river bed of Koel. The fine aggregate passed through 4.75 mm sieve and had a specific gravity of 2.68. The sand belonged to zone III as per IS standards.

### **2.1.4 Coarse Aggregates:**

The aggregates the vast majority of which are held on 4.75mm IS sieve and contains just that a lot of fine material as is allowed by the code specifications are termed as coarse aggregates. The coarse aggregates may be crushed gravel or stone obtained by the crushing of gravel or hard stone; uncrushed gravel or stone resulting from natural disintegration of rock and partially crushed gravel or stone obtained as a product of the blending of the naturally disintegrated and crushed aggregates. In our case crushed stone was used with a nominal maximum size of 20 mm and specific gravity of 2.78.

### **2.1.5 Water:**

Water is the one most essential element of cement. Water assumes the vital part of hydration of concrete which frames the coupling lattice in which the dormant totals are held in suspension medium until the grid has solidified, furthermore it serves as the lubricant between the fine and coarse aggregates and makes concrete workable.

### **2.1.6 Fiber:**

Fibre is a natural or synthetic string or used as a component of composite materials, or, when matted into sheets, used to make products such as paper, papyrus, or felt. Concrete is brittle by nature and is weak in flexure as well as direct tension therefore in order to improve this properties fibres are added to concrete. Fibres may be short discrete or in forms of rods or may be even in form of textile fibres or woven mesh fibres. Various types of fibres have been added to concrete some have high modulus of elasticity some have low modulus of elasticity each category can improve certain properties of concrete. In our case short discrete glass fibres were used and as glass fibre is susceptible to alkali we used alkali resistant glass fibres. A fiber is a material made into a long filament with a diameter generally in the order of 10  $\mu\text{m}$ . The main functions of the fibers are to carry the load and provide stiffness, strength, thermal stability, and other structural properties in the FRC.

Glass strands are filaments generally utilized as a part of the maritime and mechanical fields to create composites of medium-grade. Their unconventional trademark is their high quality. Glass is basically made of silicon ( $\text{SiO}_2$ ) with a tetrahedral structure ( $\text{SiO}_4$ ). Some aluminum oxides and other metallic particles are then included different extents to either facilitate the working operations or change a few properties (e.g., S-glass strands show a higher elasticity than E-glass).

The era development of fiberglass is fundamentally in light of turning a bunch made of sand, alumina, and limestone. The constituents are dry mixed and passed on to melting (around  $1260^\circ\text{C}$ ) in a tank. The liquefied glass is conveyed straightforwardly on platinum bushings and, by gravity, goes through specially appointed openings situated on the base. The fibers are then gathered to shape a strand ordinarily made of 204 fibers. The single fiber has a normal measurement of  $10 \mu\text{m}$  and is regularly secured with a measuring. The yarns are then packaged, much of the time without curving, in a meandering. Glass filaments are likewise accessible as slim sheets, called mats. A mat may be made of both long persistent and short strands (e.g., irregular filaments with an ordinary length somewhere around 25 and 50 mm), haphazardly organized and kept together by a concoction bond. The width of such tangles is variable between 5 cm and 2 m, their thickness being around  $0.5 \text{ kg/m}^2$ . Glass filaments normally have a Young modulus of versatility lower than carbon or aramid strands and their scraped area resistance is moderately poor; consequently, alert in their control is needed. Likewise, they are inclined to crawl and have low exhaustion quality. To upgrade the bond in the middle of filaments and grid, and to secure the strands itself against soluble operators and dampness, strands experience estimating medicines going about as coupling specialists. Such medicines are helpful to improve

toughness and weakness execution (static and element) of the composite material. FRP composites taking into account fiberglass are normally meant as GFRP.

### **2.1.7 Admixture:**

Admixtures are the chemical compounds that are used in concrete other than hydraulic cement (OPC), water and aggregates, and can also be called as mineral additives that are added to the concrete mix just before or during blending to adjust one or more of the particular properties of the concrete in the fresh or hardened state. The utilization of admixture is necessary to offer a change which is not financially achievable by changing the extents of water, cement and though not influencing the performance and durability of the concrete. Usually used admixtures are accelerating admixtures, retarding admixture, air-entraining admixtures and water-reducing admixture. In our case a water reducing admixture was used to obtain the desire workability as with increase in fibre content the mixture was becoming stiffer.

The experimental work consists of casting cubes, cylinders and prisms to study the effect of glass fibres on the compressive, flexural and split tensile strength of concrete. The effect was studied by varying the fibre content from 0% to 0.3%, no water reducing admixture was used for the experimental programme. To check the effect on concrete for fibre content variation 6 specimens each of cube, prisms and cylinders were casted. Test were conducted on the specimen after 7days and 28 days.

Further in order to get a practical use of glass fibres in concrete, concrete tiles were casted. The size of the tiles being 400mm\*400mm\*20mm. The maximum size of aggregates used for 8mm in case of tiles and the testing for tiles were done as per IS 1237:2012. The fibre content varied from 0% to 0.7% and the main study of interest was compressive strength, wet transverse strength and water absorption.

### **2.2 Casting Of Tiles:**

The tiles were prepared as per the guidelines of IS 1237:2012. The size chosen was one of the standard sizes mentioned in the code. The size was 400mm\*400mm\*20mm. The tiles were prepared from a mixture of Portland slag cement, natural aggregates and after casting this tiles were vibrated. The tiles were single layered and utmost care was taken to prepare them so that thickest and thinnest tile in the sample when compared did not exceed 10% of the minimum thickness. The mix was prepared by machine and then the mix prepared was poured in the moulds one at a time and then first they were hand compacted after that vibrated on the vibrator table. The surface finishing was done by using a finishing trowel. After pouring in the moulds and compacting on the vibrator table the moulds were put down on the surface and allowed to set for 24hrs. The mould for casting tiles is shown in figure 1.



*Figure 1 Mold for casting of tiles*

### **2.3 Materials For Casting:**

#### **2.3.1 Cement:**

Portland slag cement (PSC) – 43 grade (Kornak Cement) was used for the experimental programme. It was tested for its physical properties in accordance with IS standards.

#### **2.3.2 Fine Aggregates:**

The fine aggregates used for experimental programme was obtained from bed of river Koel. The fine aggregates used passed through 4.75mm sieve and had a specific gravity of 2.68. The fine aggregates belonged to Zone III according to IS 383 .

#### **2.3.3 Coarse Aggregates:**

The coarse aggregates used were non-reactive and as per the requirements to produce a good and durable concrete .The coarse aggregates were of two different grading and as such a definite mix proportion was used to obtain the desire grading for coarse aggregates. One grade has maximum size of 10mm and minimum 4.75mm and for the other the maximum size was 20mm and minimum 10mm. This combination was used for casting cubes, cylinders and prisms. For casting cement and concrete tiles a maximum size of 8mm and retained on 4.75mm was used. The coarse aggregates for casting tiles was obtained by sieving 10mm down aggregates.

#### **2.3.4 Water:**

Ordinary tap water which is safe and potable for drinking and washing was used for producing all types of mix.

### **2.3.5 Glass Fibers:**

Glass fiber also known as fiberglass is made from extremely fine fibres of glass. It is a light weight, extremely strong and a robust material. Glass fibres are relatively less stiff and made from relatively less expensive material as compared to carbon fibres. It is less brittle and also has lower strength than carbon fibers. There are various types of glass fibers:

1. A-glass: Also known as alkali glass and is made from soda lime silicate.
2. AR-glass: Alkali resistant glass and is made from zirconium silicates. This type of glass fibers are used in cement substrates.
3. C-glass: This type of glass fibers are used in acid corrosive environments. Made from calcium borosilicate's.
4. D-glass: Low dielectric constant made with borosilicate's.
5. E-glass: This glass fibers have very high electrical resistance and are very commonly used.
6. ECR-glass: An E-glass which has higher acid corrosion resistance.
7. R-glass: It is a support glass and is utilized where higher quality and corrosive erosion resistance is needed.
8. S-glass: Also known as structural glass and are in use where high quality, high firmness, compelling temperature resistance and destructive resistance is required.

In our case AR-glass fibers were used. The glass fibers used had a density of 2.7 gm/cm<sup>3</sup>, tensile strength 1700 MPa and Young's Modulus 72GPa.

### **2.3.6 Form Work:**

Form work may be defined as a temporary structure or a permanent structure used to contain poured concrete in fresh state. Fresh concrete is plastic and can be easily moulded. Formwork plays an important role in shaping the concrete and also support it until it gains sufficient strength to support itself. It is required that the formwork be sufficiently strong to take the dead load and live load that may come upon it during construction and also it should be sufficiently rigid at the same time to avoid bulging, twisting, swaging due to these loads. Dead loads refer to the load or weight of the forms and the weight of the fresh concrete. The live loads may be taken as the weight of the workers, equipments, runways and material storage and compacting equipments.

In our case permanent moulds were used which are commercially available in market. However for preparation of tiles moulds were specially ordered and procured from local steel fabricating shops.

### **2.4 Mixing Of Concrete:**

In order to obtain a uniform mix thorough mixing of concrete is necessary. Concrete can be produced in two ways either by hand mixing or machine mixing. Hand mixing can be done on a plane levelled surface such as a wooden platform or a paved surface having tight joints so as to prevent paste loss. To do mixing first the surface is cleaned and then moistened after that sand is first poured on the surface and then cement is spread on the sand after that thorough mixing is done. When the cement and sand gets uniformly mixed coarse aggregates are spread over the uniform sand and cement mix and then again mixed thoroughly. To mix the materials either a hoe or a square-pointed D-handled shovel is used. Dry materials are mixed until the colour of the mixture is uniform. Having obtained uniform coloured dry mix water is slowly added and the mix is again turned at least three times after completely the entire mixing process fresh concrete is produced which is plastic and can be moulded as per our needs.

In our investigation machine mixing was done to produce the fresh concrete. First the machine drum was cleaned and then moistened so as to prevent any loss of water as we are adding only a calculated amount and no extra water is added. All the dry materials are put in the drum and then dry mixed by rotating the drum when a thorough mix is obtained glass fibres are added as per the calculated which is a percent of total weight of concrete and then the materials are mixed thoroughly. After that water is added and mixed again until a uniform coloured mix is obtained. After completing all this process the concrete is dropped on a flat and clean plate from where we take it and fill our moulds.

### **2.5 Compaction:**

All specimens were first filled in their respective moulds and then hand compacted using a rod of 30mm diameter in three layers by tamping 20 times on each layer. To attain full compaction the specimens were then vibrated on a vibrator table. The tiles were prepared by putting the concrete in the mould and then hand tamping using a plane surfaced wooden block and then the mould was held tight by hands and vibrated on the vibrator table. The surface was levelled, finished and smoothed by metal trowels.

### **2.6 Curing Of Concrete:**

A significant part of the physical properties of cement rely on upon the degree of hydration of bond and the resultant microstructure of the hydrated concrete. As a result of hydration a random three dimensional structure is gradually formed which fills the space occupied by water. The hardened cement paste has a porous

structure and the pores can be divided into two categories as gel pores and capillary pores. Hydration of cement takes place only when the capillary pores remain saturated. Curing is necessary to make the concrete more durable, strong, impermeable and resistant to abrasion and frost. Curing is done by spraying water or pond curing or keeping them packed under moist gunny bags so as to prevent the loss of moisture from the surface and inside. Curing starts as soon as the concrete reaches its final set. It is generally recommended to do curing for at least 14 days to attain at least 90% of the expected strength. In our case pond curing method was used for all specimens including the tiles.

### **III. EXPERIMENTAL SETUP**

Various tests conducted on the specimens are described below along with the description and importance. There were two ways in which the investigation was carried out one in which only cubes, cylinders and prisms were casted and the grade of concrete was M-20. The proportioning of the concrete was . The nominal maximum size of aggregate was 20mm and no admixture was used.

#### **3.1 Compressive strength:**

The most important property of concrete is its compressive strength and durability. Concrete is mostly used in construction where load transferred is mostly via compressive strength. In order to check the effect of fibres on the compressive strength of concrete 150mm cubes were cast and tested. The cubes were tested at the age of 7 days and 28 days and the variation was noted.

Fibre content was varied from 0% to 0.3% when the nominal maximum size of aggregates was 20mm and no admixture was used. The water cement ratio was fixed at 0.5. The workability of the mix was observed to come down but however no extra water was used.

#### **3.2 Split Tensile Strength:**

Concrete may be subjected to tension in very rare cases and is never designed to resist direct tension. However, the load at which cracking would occur is important and needs to be determined. The tensile strength of concrete as compared to its compressive strength is very low and is found to be only 10-15 % of the compressive strength. There are various factors which influence the tensile strength of concrete like aggregates, age, curing, air-entrainment and method of test. To conduct the split tension test a cylindrical concrete specimen is loaded along its length as a result of the loading tensile stresses are developed along the central diameter along the lateral direction. The specimen splits into two when the limiting tensile strength is reached and this value can be calculated from the load given below

A diagram is shown to show how the test is carried out:

#### **3.3 Flexural Strength:**

Flexural strength is also a measure of the tensile strength of concrete. In practical concrete may not be subjected to direct tension but it is subjected to flexure in many cases particularly in beams which is a flexural member. Flexural strength is also referred to as modulus of rupture.

#### **3.4 Tests carried out on Cement and Concrete Tiles:**

Cement and concrete flooring tiles are tested as per IS 1237:2012 There are various tests given in the code but we have done the water absorption test and wet transverse strength. Other tests that were conducted on the tiles was the pulse velocity test which is a non-destructive test and predicts the quality but not the grade of concrete. The IS code does not say anything about the compressive strength test but however in order to check the compressive strength six 100mm cubes were cast and tested at 7 days and 28 days.

#### **3.5 Water absorption test:**

Six tiles were immersed in water for 24hrs, than the tiles were taken out and wiped dry. Each tile was immediately weighted after saturation. The tiles were then placed in an oven at 65°C for 24 hrs and then cooled and reweighed at room temperature.

Water absorption was calculated using the formula as given below:

$$((M1 - M2) / M2) \times 100$$

Where

M1= mass of the saturated specimen;

M2= mass of the oven-dried specimen.

#### **3.6 Wet Transverse Strength Test:**

In order to determine the wet transverse strength of tiles six full sized tiles are tested at 28 days as per the guidelines given by IS 1237:2012. Before performing the test the tiles are soaked in water for 24 hrs and then placed horizontally on two parallel steel supports, the wearing surface is upwards and its sides parallel to supports. The load is applied in such a way that the steel rod is parallel to supports and midway between them. It is required that the length of the supports and of the loading rod shall be longer than the tile. The diameter of the

loading rod shall be 12mm and be rounded. The load is applied at a uniform rate of 2000N/min, until the tile breaks. The wet transverse strength is calculated using the formula given in IS code as given below:

$$(3PI/2bt^2) N/mm^2$$

Where,

P = breaking load in N;

I = span between supports, in mm;

b = tile width, in mm; and

t = tile thickness, in mm.

### 3.7 Compressive Strength:

To get the compressive strength variation due to glass fibres 100mm cubes were cast with the same mix as used for casting concrete tiles with the same amount of admixtures. Six 100mm cubes were cast for each fibre content. Three cubes were tested at 7days and three at 28 days. The compressive test was done on universal testing machine. The cubes were cured using pond curing method and before testing they were allowed to surface dry. The formula used for calculating compressive strength is given below:

$$c = (P/A) N/mm^2$$

Where,

P=load in Newton (N) at which failure occurs,

A=surface area in mm<sup>2</sup>.

### 3.8 Pulse Velocity Test:

The pulse velocity test is a non-destructive test and is covered in IS 13311 (Part 1) – 1992. It gives a measure of the quality of concrete. The underlying principle of this test is : –

The method consists of measuring the time of travel of an ultrasonic pulse passing through the concrete being tested. Comparatively higher velocity is obtained when concrete quality is good in terms of density, uniformity, homogeneity etc. First couplant is applied to the surfaces of the transducers and pressed hard onto the surface of the material. The transducers are not moved while a reading is being taken, as this can generate noise signals and errors in measurements. The transducers are continuously held onto the surface of the material until a consistent reading appears on the display, which is the time in microsecond for the ultrasonic pulse to travel the distance 'L'. The mean value of the display readings is taken when the unit's digit hunts between two values. The velocities obtained can be interpreted in the form of quality of concrete and not in form of the grade of concrete.

$$\text{Pulse velocity} = (\text{Path length}/\text{Travel time})$$

### 3.9 Procedure:

Experiments started with the preliminary tests on material properties as per the Indian standards. Composites being made of cement, fiber and sand as major components tests were conducted for standardizing properties of these materials. Tests of physical properties of sand, cement and fiber were conducted first and then they were used in the research. NO tests were conducted on water as ordinary tap water from govt. water supply was used throughout the research work.

**Specific gravity test:** The test was conducted as per IS 2720-part iii to obtain the specific gravity of cement. The specific gravity of cement was found to be 3.10.

**Consistency Test:** As per IS 4031-part iv 1988 a consistency test was done on the cement using Vicat's apparatus confirming to IS 5513 .The standard consistency was found to be 30%.

**Fineness test :** Fineness of the cement was tested as per IS 4031-part 1 by the method of sieve analysis. A 10g sample of cement was agitated for 2 mins over a 90 micron sieve . The test results proved that almost all the cement passed through the sieve and negligible weight of dust was retained.

**Test for the grade of cement (Compressive strength test):** AS per the guidelines of IS 4031-part vi 1988 cubes of cement mortar were casted at water content of ( P/4 + 3 %) of total dry mass taken and were tested for 7 day and 28 day strength. For simplicity ,3 day strength test was omitted .until tests the casted cubes were kept in water for curing.The minimum 7 daycompressive strength averaged over three cubes was 24.33 MPa and 28 day strength averaged over three cubes was 41.67MPa.

### 3.10 Test on sand:

**Specific gravity test:** The specific gravity of sand was measured using a pycnometer by the procedure confirming to IS 2386 part iii-1963.The specific gravity was found to be 2.66 .

**Sieve analysis of sand :** In order to ascertain the particle sine distribution of sand Dry sieve analysis was carried out. The sieve sizes were as per IS 2386-part I. The zone of sand was zone iii.

**3.11 Preparation of M-20 grade concrete:**

M-20 grade concrete was prepared using the mix design guidelines as per IS -10262 without using admixture. A water cement ratio of 0.50 was adopted as fibre reduces the workability of concrete to a great extent. Maximum .3% chopped fibres by weight of concrete were added to check the effect of fibres on the properties of concrete as even at 0.3 % the concrete turned very harsh and a great deal of vibration was needed. Total 4 different batches of M-20 grade concrete was prepared with 0, 0.1, 0.2 and 0.3 percent fibres

**IV. RESULTS**

The results obtained are shown below in tabular form.

**4.1 Compressive Strength of Concrete (in N/mm<sup>2</sup>) :**

The 7 days compressive strength was studied and the values of 3 samples studied are shown in the tabular form. Table 1 shows the data of 7 days compressive strength obtained. Table 1 gives the 7 day compressive strength of concrete with maximum nominal size of aggregates 20mm.

*Table 1 7days compressive strength of concrete*

Serial number	Without fibre	0.1% fibre	0.2%	0.3%
1	16.89	17.77	21.33	22.22
2	16.44	17.33	20.88	22.67
3	16.44	17.33	21.33	23.11

The 28 days compressive strength was studied and the values of 3 samples studied are shown in the tabular form. Table 2 shows the data of 28 days compressive strength obtained. Table 2 gives the 28 days compressive strength of concrete with maximum nominal size of aggregates 20mm.

*Table 2 28 days compressive strength of concrete*

Serial number	Without fibre	0.1%	0.2%	0.3%
1	25.33	28	28.88	30.22
2	25.77	31	28.88	28.88
3	25.33	28	31	30.66

**4.2 Split Tensile Strength comparison (in N/mm<sup>2</sup>) :**

The 7 days Split Tensile strength was studied and the values of 3 samples studied are shown in the tabular form. Table 3 shows the data of 7 days compressive strength obtained. Table 3 gives the 7 days compressive strength of concrete with maximum nominal size of aggregates 20mm.

*Table 3 7days Split Tensile Strength of Concrete*

Serial number	Without fibre	0.1%	0.2%	0.3%
1	1.485	1.84	2.405	2.405
2	1.626	1.70	2.26	2.405
3	1.45	1.84	2.26	2.263

The 28 days Split Tensile strength was studied and the values of 3 samples studied are shown in the tabular form. Table 4 shows the data of 28 days compressive strength obtained. Table 4 gives the 28 days compressive strength of concrete with maximum nominal size of aggregates 20mm.

*Table 4 28 days Split Tensile Strength of Concrete*

Serial number	Without fibre	0.1%	0.2%	0.3%
1	2.829	2.83	2.97	2.97
2	2.76	2.83	2.97	2.97
3	2.829	2.97	3.35	2.97

**4.3 Flexural Tensile Strength (in N/mm<sup>2</sup>):**

The 7 days Flexural Tensile strength was studied and the values of 3 samples studied are shown in the tabular form. Table 5 shows the data of 7 days flexural tensile obtained. Table 5 gives the 7 day compressive strength of concrete with maximum nominal size of aggregates 20mm.

*Table 5 7 days Flexural Strength of Concrete*

Serial number	Without fibre	0.1%	0.2%	0.3%
1	4.6	4.744	4.988	5.744
2	4.7	4.776	4.988	5.424
3	4.8	4.756	4.9	5.704

The 28 days flexural tensile strength was studied and the values of 3 samples studied are shown in the tabular form. Table 6 shows the data of 28 days compressive strength obtained. Table 6 gives the 28 days flexural tensile strength of concrete with maximum nominal size of aggregates 20mm.

*Table 6 28 days Flexural Strength of Concrete*

Serial number	Without fibre	0.1%	0.2%	0.3%
1	5.104	6.368	7.544	7.156
2	5.204	6.456	7.104	7.96
3	5.242	6.652	6.844	8.32

**4.4 Tests carried out on cement and concrete tiles:**

Cement and concrete tiles were tested as per IS 1237:2012. The test performed were wet transverse strength, water absorption test. Compressive strength test is not mentioned in the code but it was performed as fibers can reduce the strength of the concrete. Pulse velocity test and natural frequency test were also conducted. The results obtained are given below in tabular form:

**4.4.1 Compressive strength test:**

The 7 days compressive strength was studied and the average values of 3 samples studied are shown in the tabular form. Table 7 shows the data of 28 days compressive strength obtained. Table 7 gives the 7 days compressive strength of concrete with maximum nominal size of aggregates 8mm.

*Table 7 7 days Compressive Strength of Concrete*

Fibre content(% of the total weight of concrete)	WEIGHT(KG)	Average 7 days compressive strength (N/mm <sup>2</sup> )
0	2.495	32
0.1	2.478	28
0.2	2.478	30
0.3	2.500	31
0.4	2.487	28
0.5	2.500	27
0.6	2.400	26
0.7	2.390	25

The 28 days Compressive strength was studied and the average values of 3 samples studied are shown in the tabular form. Table 8 shows the data of 28 days compressive strength obtained. Table 8 gives the 28 days compressive strength of concrete with maximum nominal size of aggregates 8mm.

*Table 8 28 days Compressive Strength of Concrete*

Fibre content(% of the total weight of concrete)	WEIGHT(KG)	Average 28 days compressive strength (N/mm <sup>2</sup> )
0	2.495	45
0.1	2.478	37
0.2	2.478	37

0.3	2.500	36
0.4	2.487	38
0.5	2.500	33
0.6	2.400	32
0.7	2.390	31

**4.4.2 Wet transverse strength:**

The 28 days flexural tensile strength was studied and the average values of 3 samples studied are shown in the tabular form. Table 9 shows the data of 28 days wet transverse strength obtained. Table 9 gives the 28 days wet transverse strength of concrete with maximum nominal size of aggregates 8mm.

*Table 9 28 days Wet Transverse Strength of Concrete*

Fibre content(% of the total weight of concrete)	Average 28 day transverse strength (N/mm <sup>2</sup> )
0	1.41
0.1	1.64
0.2	1.72
0.3	1.87
0.4	1.944
0.5	2.24
0.6	2.39
0.7	2.542

**4.4.3 Water absorption:**

The water absorption of concrete after 28 days was studied and the average water absorption values of 6 samples obtained are shown in the tabular form. Table 10 shows the data of 28 days water absorption obtained. Table 10 gives the 28 days water absorption of concrete with maximum nominal size of aggregates 8mm.

*Table 10 28 days Water Absorption of Concrete*

Fibre content(% of the total weight of concrete)	Average water absorption after 28 days (%)
0	2.69
0.1	2.30
0.2	1.95
0.3	1.57
0.4	1.22
0.5	1.19
0.6	1.17
0.7	1.02

**4.4.4 Pulse Velocity test:**

Pulse velocity test was carried out on the tiles and the average values of the velocities which were not varying more than 15% are reported and the implications are shown in Table 11

*Table 11 Obtained Pulse velocity*

Fibre content(% of the total weight of concrete)	Average velocity(m/s)
0	4497
0.1	4800
0.2	4365
0.3	4612
0.4	4395
0.5	4458
0.6	4386
0.7	4436

**V. CONCLUSIONS**

In this experimental program the effect of short discrete glass fibers on the compressive, split tensile strength and flexural strength of concrete was studied. The effect of glass fibres on cement and concrete tiles which are produced by vibration method are also studied. The properties studied are compressive strength, wet transverse strength and water absorption. The concrete mix gets harsher and less workable with increase of fiber

content therefore use of admixture become necessary. However even after giving dosage of admixture as high as 1.5% proper workability could not be obtained and some segregation was observed. Therefore it was not possible to go beyond 0.7% fiber content.

The various observation based on the experimental result are as follows:

1. The compressive strength of concrete without admixture is not affected by the presence of short discrete glass fibers with fibre content in the range 0.1 to 0.3 % of fiber content by weight of concrete.
2. The split tensile strength of concrete increases with the addition of glass fibers.
3. The flexural strength of concrete increases with increase in fiber content and as such the tension carrying capacity of concrete may increase in flexure
4. The wet transverse strength of tiles increases and the increase has been found with addition of fibers
5. The water absorption of the concrete also decreases with increase in fiber content.
6. The compressive strength of concrete with admixture was not affected upto 0.4 % fiber content but decreased with the presence of higher amount of fibers.

## REFERENCES

- [1]. Cook D.J., Pama R.P., Weerasinghe H.L.S.D. "Coir fibre reinforced cement as a low cost roofing material". *Build Environ* 1978;13(3):193–8.
- [2]. Perez-Pena .M and Mobasher .B, "Mechanical properties of fiber reinforced lightweight concrete composites ". *Cement and Concrete Research*, Vol. 24, No. 6, pp. 1121-1132, 1994
- [3]. Brandt AM."Cement-based composites: materials, mechanical properties and performance". London: E&FN Spon; 1995. p. 470
- [4]. Nakamura H, Mihashi H. "Evaluation of tension softening properties of fiber reinforced cementitious composites." *Fracture Mechanics of Concrete Structures* 1998; I:499e510.
- [5]. Mirza F.A., Soroushiannd P. "Effects of alkali-resistant glass fiber reinforcement on crack and temperature resistance of lightweight concrete." *Cement and Concrete Composites* 2002;24(2):223–7
- [6]. Robert S.P. Coutts ."A review of Australian research into natural fibre cement composites" *Cement & Concrete Composites* 27 (2005) 518–526
- [7]. Khosrow Ghavami. "Bamboo as reinforcement in structural concrete elements".*Cement & Concrete Composites* 27 (2005) 637–649
- [8]. Huang Gu, Zuo Zhongge "Compressive behaviour of concrete cylinders reinforced by glass and polyester filaments". *Materials and Design* 26 (2005) 450–453
- [9]. Andrzej Brandt .M "Fibre reinforced cement-based (FRC) composites after over 40 years of development in building and civil engineering". *Composite Structures* 86 (2008) 3–9
- [10]. Luiz C. Roma Jr., Luciane S. Martello, Holmer Savastano Jr. "Evaluation of mechanical, physical and thermal performance of cement-based tiles reinforced with vegetable fibers". *Construction and Building Materials* 22 (2008) 668–674
- [11]. Filho Toledo Dias Romildo, Andrade Silva Flavio de, Fairbairn E.M.R.."Durability of compression molded sisal fiber reinforced mortar laminates". *Construction and Building Materials* 23 (2009) 2409–2420
- [12]. Wu. Y.-F. "The structural behaviour and design methodology for a new building system consisting of glass fiber reinforced gypsum panels" *Construction and Building Material* 23 (2009) 2905–2913
- [13]. Swami B.L.P. , "Studies on glass fiber reinforced concrete composites – strength and behaviour Challenges", *Opportunities and Solutions in Structural Engineering*,2010,pp-1-1
- [14]. Tonoli G.H.D., S.F. Santos,A.P. Joaquim,H. Savastano Jr "Effect of accelerated carbonation on cementitious roofing tiles reinforced with lignocellulosic fibre" *Construction and Building Materials* 24 (2010) 193–201
- [15]. Enfedaque .A, D. Cendon, F. Galvez , Sanchez-Galvez .V,"Failure and impact behavior of facade panels made of glass fiber reinforced cement(GRC)". *Engineering Failure Analysis* 18 (2011) 1652–1663.
- [16]. Mohamed S. Issa, Ibrahim M. Metwally, Sherif M. Elzeiny "Influence of fibers on flexural behavior and ductility of concrete beams reinforced with GFRP rebars" *Engineering Structures* 33 (2011) 1754–1763.
- [17]. Sung-Sik Park "Unconfined compressive strength and ductility of fiber-reinforced cemented sand." *Construction and Building Materials* 25 (2011) 1134–1138
- [18]. Majid Ali , Anthony Liu, Hou Sou, Nawawi Chow "Mechanical and dynamic properties of coconut fibre reinforced concrete" *Construction and Building Materials* 30 (2012) 814–825
- [19]. Frank Schladitz , Michael Frenzel , Daniel Ehlig "Bending load capacity of reinforced concrete slabs strengthened with textile reinforced concrete" *Engineering Structures* 40(2012) 317–326
- [20]. Shasha Wang, Min-Hong Zhang, Ser Tong Quek "Mechanical behavior of fiber-reinforced high-strength concrete subjected to high strain-rate compressive loading" *Construction and Building Materials* 31 (2012) 1–11
- [21]. Alberto Meda , Fausto Minelli, Giovanni A. Plizzari "Flexural behaviour of RC beams in fibre reinforced concrete" *Composites: Part B* 43 (2012) 2930–2937
- [22]. Funke H. , Gelbrich .S , Ehrlich .A "Development of a new hybrid material of textile reinforced concrete and glass fibre reinforced plastic" *Procedia Materials Science* 2 (2013 ) 103 – 110
- [23]. Xiangming Zhou, Seyed Hamidreza Ghaffar, Wei Dong, Olayinka Oladiran, Mizi Fan "Fracture and impact properties of short discrete jute fibre-reinforced cementitious composites" *Materials and Design* 49 (2013) 35–47
- [24]. Mohammad Sayyar , Parviz Soroushian "Low-cost glass fiber composites with enhanced alkali resistance tailored towards concrete reinforcement" .*Construction and Building Materials* 44 (2013) 458–463
- [25]. Gowri .R, Angeline Mary.M., "Effect of glass wool fibres on mechanical properties of concrete". *International Journal of Engineering Trends and Technology (IJETT) - Volume4 Issue7- July 2013*.

- [34]. Foglar Marek, Kovar Martin. "Conclusions from experimental testing of blast resistance of FRC and RC bridge decks". *International Journal of Impact Engineering* 59 (2013)18e28
- [35]. Bonakdar .A, Babbitt F., Mobasher B. "Physical and mechanical characterization of Fiber-Reinforced Aerated Concrete (FRAC)". *Cement & Concrete Composites* 38 (2013)82–91
- [36]. Chanaka M. Abeysinghe, David P. Thambiratnam , Nimal J. Perera "Flexural performance of an innovative Hybrid Composite Floor Plate System comprising Glass– fibre Reinforced Cement, Polyurethane and steel laminate" *Composite Structures* 95(2013) 179–190
- [37]. Tassew S.T., Lubel A.S. , "Mechanical properties of glass fiber reinforced ceramic concrete". *Construction and Building Materials* 51 (2014) 215–224.
- [38]. Dey V., Bonakdar A., Mobasher B. "Low-velocity flexural impact response of fiber-reinforced aerated Concrete". *Cement & Concrete Composites* 49 (2014) 100–110
- [39]. Pantelides C.P., Garfield T.T., Richins W.D., Larson T.K., Blakeley J.E. "Reinforced concrete and fiber reinforced concrete panels subjected to blast detonations and post-blast static tests". *Engineering Structures* 76 (2014) 24–33.
- [40]. Agarwal Atul ,Nanda Bharadwaj ,Maity Damodar. "Experimental investigation on chemically treated bamboo reinforced concrete beams and columns". *Construction and Building Materials* 71 (2014) 610–617
- [41]. Raphael Contamine, Angel Junes , Amir Si Larbi "Tensile and in-plane shear behaviour of textile reinforced concrete: Analysis of a new multiscale reinforcement". *Construction and Building Materials* 51 (2014) 405–413
- [42]. Wai Hoe Kwan , Mahyuddin Ramli, Chee Ban Cheah "Flexural strength and impact resistance study of fibre reinforced concrete in simulated aggressive environment". *Construction and Building Materials* 63 (2014) 62–71
- [43]. Mobasher Barzin, Dey Vikram, Zvi Cohen,Alva Peled "Correlation of constitutive response of hybrid textile reinforced concrete from tensile and flexural tests" *Cement & Concrete Composites* 53 (2014) 148–161.
- [44]. Ali Shams , Michael Horstmann , Josef Hegger "Experimental investigations on Textile-Reinforced Concrete (TRC) sandwich sections" *Composite Structures* 118 (2014) 643– 65